



TECHNICAL DATA SHEET



Repair Mortar: A Fine Component for Achieving Smooth & Thin Finishing.



DESCRIPTION

- **SL3**® **Conrep FF** is a one-component specially formulated mortar designed for fair face repair.
- It consists of a blend of hydraulic cements, carefully selected and graded fine aggregates, synthetic-based additives and special polymer.
- When mixed with water, **SL3**® **Conrep FF** transforms into a highly homogenous, smooth, fine and consistent mortar.
- This product does not contain iron particles, chlorides, or gypsum, ensuring that its use will not result in rust, corrosion, or raveling, even under moist conditions.

ADVANTAGES

- · Excellent workability.
- · Rapid hardening.
- Non-shrinkage material.
- High-resistant to water.
- · High bond strength ensures excellent adhesion.
- Homogenous color.
- External and internal use.

METHOD OF USE

- The areas to be repaired must be clean, sound and free of contaminants.
- Before application, saturate the surface with water, then allow it to dry.
- Any loose or deteriorated concrete should be removed using mechanical means.
- For each 20 kg bag of **SL3® Conrep FF**, add 6.5 8 liters of water.
- Mix the ingredients using a suitable electrical drill for 4-5 minutes or until a uniform lump free homogeneous mixture is obtained.
- · Allow the grout to mature for 1 min prior to pouring.
- · Apply the paste of SL3® Conrep FF using a clean steel trowel.
- Once the SL3® Conrep FF has begun to set, it can be sprayed with a small amount of water onto the surface of SL3® Conrep FF before final smoothing.
- To cure the SL3® Conrep FF, use clean water for three days by spraying twice a day.

APPLICATIONS

SL3® **Conrep FF** is utilized in all concrete finishes requiring cosmetic repair to fill small voids and thin cracks, ensuring a homogeneous appearance with the real concrete color and texture.

CHARACTERISTICS

• Consumption: 1.25 kg/m2 per 1mm thickness

• Appearance: Grey Powder

Cl- Content: Nil

Grain Size: 0 to 0.1 mm
Min. thickness: 1 mm
Max. thickness: 3 mm

TECHNICAL DATA

SL3® Conrep FF at 28 days

• Compressive Strength: 15.7 Mpa

• Flexural Strength: 6.8 mpa

• Bond Strength: 6.2

• Increase in length by: $0.068\,\%$

STORAGE

SL3® Conrep FF has a shelf life of 12 months from the date of manufacture if stored at temperatures between 2°C and 50°C, away from moisture in unopened bags.

CAUTIONS: HEALTH & SAFETY

- The product may cause skin irritation.
- It is advisable to wear gloves and goggles.
- In case of contact with eyes or mucous membranes, flush immediately with plenty of warm water and seek medical attention without delay.
- SL3® Conrep FF is nonflammable.

PACKAGING SIZE:

Bag: 50 lbs. (22.7 kg)

FOR TECHNICAL SERVICES

VELOCITY® green energy, LLC. P.O. Box16506, Irvine CA 92623, United States Contact us at: (949) 468-2742 (888) 508-6191



















End of Technical Data Sheet